


## CLIENT: RELIANCE INDUSTRIES LIMITED REGRESSION ANALYSIS ACCORDING TO ISO 9080 OF THE PE PIPE COMPOUND RELENE 46GP003 B



### INTRODUCTION

Exova offers accredited testing and evaluation according to ISO 9080, i.e. hydrostatic pressure testing followed by evaluation of the long-term hydrostatic strength and MRS-classification according to ISO 12162.

### TASK

The aim was to evaluate the compound according to ISO 9080 in order to obtain a MRS-classification according to ISO 12162 of the PE pipe compound Relene 46GP003 B from Reliance Industries Ltd.

### RESULTS OBTAINED

The evaluation was performed in accordance with ISO 9080:2003. More information can be found in Exova report P-09/26.

#### EXTRAPOLATED STRENGTH VALUES

Temp [°C]	Time [Yrs]	$\sigma_{LPL}$ [MPa]	$\sigma_{LTHS}$ [MPa]
20	50.0	10.46	10.79
20	100	10.32	10.66
60	6.00	6.58	6.84
80	1.00	5.11	5.32

Exova Nyköping Polymer  
T +46 155 20 64 78  
F +46 155 26 31 25  
E jonathan.rabiei@exova.com  
W www.polymer.exova.com



Exova Marketing centre  
T +44 161 787 3291  
F +44 161 787 3251  
E info@exova.com  
W www.exova.com

### CLASSIFICATION

MRS = 10 MPa